

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 1123 (1975): Method of identification of natural building stones [CED 6: Stones]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



Indian Standard

**METHOD OF IDENTIFICATION OF
NATURAL BUILDING STONES**

(*First Revision*)

Fourth Reprint SEPTEMBER 1998

UDC 691.21 : 552.12

© Copyright 1975

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Indian Standard

METHOD OF IDENTIFICATION OF NATURAL BUILDING STONES

(First Revision)

Stones Sectional Committee. BDC 6

Chairman

SHRI C. B. L. MATHUR

Representing

Public Works Department, Government of Rajasthan,
Jaipur

Members

SHRI K. K. AGRAWALA
SHRI K. K. MADHOK (*Alternate*)
SHRI T. N. BHARGAVA
SHRI J. K. CHARAN
SHRI K. N. SUBBA RAO (*Alternate*)
CHIEF ARCHITECT
SHRI G. C. DASS
SHRI P. R. DAS (*Alternate*)
SHRI Y. N. DAVE

SHRI R. G. GUPTA (*Alternate*)
DEPUTY DIRECTOR (RESEARCH)

DEPUTY DIRECTOR (RESEARCH), CONTROL &
RESEARCH LABORATORY
DR M. P. DHIR
SHRI R. L. NANDA (*Alternate*)
DIRECTOR, ERI

DIRECTOR (CSMRS)
DEPUTY DIRECTOR (CSMRS) (*Alternate*)
DIRECTOR, MERI

RESEARCH OFFICER, MERI (*Alternate*)
SHRI M. K. GUPTA
SHRI S. D. PATHAK (*Alternate*)
DR IQBAL ALI

SHRI A. B. LINGAM (*Alternate*)
SHRI D. G. KADKADE
SHRI V. B. DESAI (*Alternate*)
SHRI T. R. MEHANDRU
SHRI PREM SWARUP

SHRI A. K. AGARWAL (*Alternate*)
DR A. V. R. RAO
SHRI J. SEN GUPTA (*Alternate*)
DR B. N. SINHA
SHRI S. R. PRADHAN (*Alternate*)
SUPERINTENDING ENGINEER (DESIGNS)

SUPERINTENDING ENGINEER (DESIGN)

DEPUTY CHIEF ENGINEER (I&D) (*Alternate*)

Builders' Association of India, Bombay

Ministry of Shipping and Transport (Roads Wing)
Engineer-in-Chief's Branch, Army Headquarters

Central Public Works Department, New Delhi
National Test House, Calcutta

Department of Geology & Mining, Government of
Rajasthan, Udaipur

Public Works Department, Government of Uttar Pradesh,
Lucknow
Public Works Department, Government of Orissa,
Bhubaneswar
Central Road Research Institute (CSIR), New Delhi

Public Works Department, Government of Gujarat,
Baroda
Central Water Commission, New Delhi

Irrigation & Power Department, Government of
Maharashtra, Bombay

Himalayan Tiles and Marble Pvt Ltd, Bombay

Engineering Research Laboratory, Government of Andhra
Pradesh, Hyderabad

The Hindustan Construction Co Ltd, Bombay

Institution of Engineers (India), Calcutta
Department of Geology & Mining, Government of Uttar
Pradesh, Lucknow

National Buildings Organization, New Delhi

Geological Survey of India, Calcutta

Public Works Department, Government of Karnataka,
Bangalore
Public Works Department, Government of Tamil Nadu,
Madras

(Continued on page 2)

© Copyright 1975

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 1123 - 1975

(Continued from page 1)

Members

SUPERINTENDING ENGINEER (DESIGN & PLG)

SUPERINTENDING ENGINEER (PLG CIRCLE)

SUPERINTENDING SURVEYOR OF WORKS

SHRI D. AJITHA SIMHA,
Director (Civ Engg)

Representing

Public Works Department, Government of Andhra
Pradesh, Hyderabad

Public Works Department, Government of West Bengal,
Calcutta

Public Works Department, Government of Himachal
Pradesh, Simla

Director General, **BIS** (*Ex-officio Member*)

Secretary

SHRI K. M. MATHUR

Deputy Director (Civ Engg), **BIS**

Indian Standard

METHOD OF IDENTIFICATION OF NATURAL BUILDING STONES

(First Revision)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 19 July 1975, after the draft finalized by the Stones Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Building stones are available in large quantity in various parts of the country and to select and utilize them for their satisfactory performance it is necessary to know the various strength properties determined according to the standard procedure. The strength of the rocks depends on its mineral constituents which form the basis of classification

and identification of rocks and thus before ascertaining the strength properties it is also necessary to identify the types of rock. This standard had therefore been formulated to cover standard methods for identification of natural building stones. This standard was first published in 1957 which covered the aspects of petrographical examination of building stones. While revising the standard its scope is limited to only identification of natural building stones which is in fact needed by the various research laboratories of stones using departments.

1. SCOPE

1.1 This standard lays down the procedure for identification of some of common types of natural building stones.

2. SELECTION OF SAMPLE

2.1 The sample shall be selected to represent the type of grade of stone under consideration. The samples shall be from the fresh rock and not weathered.

2.2 The sample shall be selected by the purchaser or his authorised representative from the quarried stone or taken from the natural rock, as described in 2.2.1 and 2.2.2 and shall be of adequate size to permit the preparation of the requisite number of test pieces.

2.2.1 Stones from Ledges or Quarries — The ledge or quarry face of the stone shall be inspected to determine any variation in different strata. Differences in colour, texture and structure shall be observed. Separate samples of stone weighing at least 25 kg each of the specimens shall be obtained from all strata that appear to vary in colour, texture and structure. Pieces that have been damaged

by blasting, driving wedges, heating, etc, shall not be included in the sample.

2.2.2 Field Stone and Boulders — A detailed inspection of the stone and boulders over the area where the supply is to be obtained shall be made. The different kinds of stone and their condition at various quarry sites shall be recorded. Separate samples for each class of stone that would be considered for use in construction as indicated by visual inspection shall be selected.

3. PROCEDURE

3.1 The sample shall be examined macroscopically for its colour, structure, texture and mineral constituents.

3.2 The type of rocks shall be identified according to characteristics given in Table 1. In case of doubt guidance can be obtained from engineering properties of the rock given in Table 1.

4. REPORTING

4.1 Date of sample taken, identification of sample and the type of stone shall be reported.

TABLE 1 CHARACTERISTICS OF BUILDING STONES

(Clause 3.2)

Sl. No.	Type	PHYSICAL PROPERTIES			Uses	Availability	AVERAGE ENGINEERING PROPERTIES (See Note)						
		Colour	Texture & Structure	Mineralogical Composition			Specific Gravity	Compressive Strength	Shear Strength	Tensile Strength	Porosity	Resistance to Abrasion	Modulus of Elasticity
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)
								kg/cm ²	kg/cm ²	kg/cm ²	Percent	Percent	kg/cm ²
Class: Igneous Rocks													
1.	Granite*	White to light grey and pink.	Crystalline, fine to coarse grained, massive sometimes sheeted and banded; joints common.	Essentially quartz and feldspar with mica, amphiboles and pyroxenes as accessories.	Used primarily for bridge piers, river walls, dams and related structures, pavements, kerbs, pedestal, monumental buildings, institutional and commercial buildings, table top, coarse aggregate, road metal, etc. Polished granite looks more elegant than marble with a very long lasting lustre. Good foreign market.	Granites occur throughout the country. Only a relatively small number of suitable colour or texture are available. Most granites are characterised by joints and fractures. It is desired that granites shall be free from flaws, etc. Granites may be graded by their compressive strength.	2.63-2.75	1 000-2 500	140-500	70-250	0.4-4	43.9-87.9	2 × 10 ⁵ to 6 × 10 ⁵
2.	Granodiorite*	Light grey.	Crystalline, medium to coarse grained; massive; joints common.	Essential minerals are quartz and plagioclase feldspar with accessories like biotite and hornblende.	Same use as granites.	Less abundant in occurrence.	2.8-3.0	—	—	—	0.50	—	—
3.	Syenite*	Light coloured to dark green, grey and bluish grey.	Crystalline, medium to coarse grained; massive; joints common.	Essential minerals are alkali feldspar sometimes with nepheline (nepheline syenite). Common accessories are hornblende, biotite and augite.	Same use as granites.	Syenites are less abundant than granites.	2.60-2.80	350-500	—	—	1.38-1.54	—	6 × 10 ⁵ to 8 × 10 ⁵
4.	Diorite*	Grey to dark grey.	Crystalline, medium to coarse grained; massive; joints common.	Essential minerals are plagioclase feldspar and dark minerals.	Used as a good aggregate material and road metal, etc.	Found in a number of places in India.	2.8-3.0	1 800-3 000	—	150-300	0.25	—	7 × 10 ⁵ to 10 × 10 ⁵
5.	Gabbro*	Dark grey to black.	Crystalline, medium to coarse grained; banded and often jointed.	Consists of lime-feldspar and pyroxene (augite); accessories may be olivine, biotite, hornblende and rarely quartz.	May be used where available for bridge piers, river walls dam and related structures; it may also be used for pavements, kerbs and in buildings (same as granite).	It's high strength value and low porosity, makes it suitable for heavy structures.	2.90-3.2	1 800-3 000	—	150-300	0.1-0.2	—	7 × 10 ⁵ to 11 × 10 ⁵

6.	Basalt (Deccan Trap)†	Dark grey to black.	Medium to fine grained, dense and compact and also at times vesicular with flow bands. Often occurring in columns and prismatic structures. Fractures and joints common.	Plagioclase feldspar and pyroxene with or without interstitial glass; olivine, sometimes common. Vesicles filled by quartz, calcite and zeolite.	Used primarily for bridge piers, river walls, dams and related structures, in masonry works and is used also for pavements, kerbs, monumental buildings; etc.	Basalts occur as "trap" rocks in western India, and in Rajmahal. It is cut into slabs and blocks. The presence of void, infilling of calcite, zeolite and quartz are undesirable. Fractures, joints also decrease its importance. Basalt generally have a dark brown appearance.	2-6-3-0	1 500-3 000	200-600	100-300	0-1-1-0	14-86-18-92	6 × 10 ³ to 10 × 10 ³
7.	Dolerite†	Dark grey to black	Crystalline, fine to coarse grained; joints and fractures common.	Consists of plagioclase feldspar and pyroxene; olivine, hornblende and biotite are common accessories.	Same as Gabbro.	It's high strength values and low porosity makes it suitable for heavy structures. But joints may not allow large homogeneous block and slabs to be cut from quarries. Makes a very high quality aggregate material.	3-0-3-05	2 000-3 500	250-600	150-350	0-1-0-5	—	8 × 10 ³ to 11 × 10 ³
8.	Rhyolite†	White to light, grey, pink and greyish black; black when extremely glassy (obsidian and pitchstone).	Glassy to cryptocrystalline with few embedded crystals of quartz and feldspars; flowbands, and fractures quite common.	A volcanic equivalent of granite.	Though not used on large scale; rhyolite may be used as blocks if easily available; in buildings, paving blocks, ornamental and decorative works, etc.	Rhyolites are less abundant than granites. The rock may be characterised by cracks and fractures which render the blocks unsuitable for the purpose of building stone.	2-40-2-60	—	—	—	4-6	—	—
9.	Trachyte†	Grey to bluish grey.	Glassy, aphanitic; flowbands and fractures common.	A volcanic equivalent of syenite.	Used as a building stone — dimension stone, grinding stone (same as granite).	Fairly abundant in occurrence.	2-60-2-35	820	—	—	—	19-5	—
10.	Andesite†	Dark grey to black.	Glassy, aphanitic.	A volcanic rock with plagioclase feldspar and one or more minerals like biotite pyroxene and hornblende.	Not generally in use, but may be used, if easily available, as blocks and slabs in buildings paving blocks ornamental and decorative works, etc.	It is not abundant in India. May possess cooling cracks, joints and fractures which may render it unsuitable as a building stone.	2-20-2-60	1 300-2 500	—	—	0-10-11	—	—
Class: Sedimentary Rocks													
1.	Sandstone	Depends on the colour of matrix and cement; generally white, grey, red, buff, brown, yellow and even dark grey.	Stratified (bedded) fine to coarse grained; cross-bedding flute-cast and sole-markings, etc., common.	Consists mainly of quartz with feldspar and dark minerals in a siliceous, calcareous, argillaceous and ferruginous cement.	Used for masonry work, for dams, bridge piers, river walls, buildings, pavements, kerbs, monumental stones, etc.	Famous building stone, ornamental stone. Weathering of the rock renders it unsuitable as building stone. Kaolinisation of feldspars and leaching effect of matrix and cement make the rock porous. It is desirable to use sandstone with silica cement for heavy structures if necessary.	1-85-2-7	200-1 700	80-400	40-250	5-25	1-6-29-0	0-5 × 10 ³ to 8-0 × 10 ³

* These fall under 'Granite Group'.

† These fall under 'Basalt Group'.

(Continued)

TABLE 1 CHARACTERISTICS OF BUILDING STONES — *Contd*

Sl. No.	Type	PHYSICAL PROPERTIES			USES	AVAILABILITY	AVERAGE ENGINEERING PROPERTIES (See NOTE)						
		Colour	Texture & Structure	Mineralogical Composition			Specific Gravity	Compressive Strength	Shear Strength	Tensile Strength	Porosity	Resistance to Abrasion	Modulus of Elasticity
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)
								kg/cm ²	kg/cm ²	kg/cm ²	Percent	Percent	kg/cm ²
2.	Limestone and dolomite	White, grey, pink, red, blue, buff brown, green yellow, black, etc. (Colour due to impurities in the form of silicates and carbonates).	Bedded, granular; fine grained.	Consists essentially of calcite (calcium carbonate) with varying amounts of magnesium carbonate.	Generally used as slabs and tiles in any type of construction used in buildings. Also large size blocks of Mililite limestone (Porbandar stone) used as ornamental and building stone.	Limestone is found to occur throughout India. It should be devoid of any argillaceous band, softer vein, cracks	2.14-2.8 (limestone) 2.5-2.8 (dolomite).	300-2 500 (limestone) and (dolomite).	100-500	50-250	5-20	1.3-24.1	1.0 × 10 ⁶ to 8.0 × 10 ⁶
3.	Laterite	Brownish red, yellow, brown, grey and mottled colours.	Porous, oolitic and pisolitic with cavities; at times bedded.	A mixture of hydrated oxides of iron and aluminium frequently with manganese dioxide, titanium oxide and free silica.	Generally used as blocks in the construction of buildings, institutional and commercial buildings.	Freshly quarried laterite is soft and porous, but when exposed to atmospheric conditions it hardens and makes a very tough material. When used in walls it should be plastered from outside.	1.85	19-23	—	—	—	—	—
Class: Metamorphic Rocks													
1.	Charnnockite	Light grey to dark grey.	Fine to coarse grained, massive banded and sometimes foliated.	Consists of quartz, feldspar, hypersthene and garnet.	Generally used as slabs and block in the construction of building, monuments, pavements, kerbs, etc, form a source of aggregate material.	Occurs in association with Khondalites in the Eastern Ghats. Its strength is similar to granites and may be put to similar uses as granite.	2.7-3.0	—	—	—	—	—	7.94 × 10 ⁵ to 9.94 × 10 ⁵
2.	Gneisses	Light grey, pink, purple, greenish grey and dark grey.	Fine to coarse grained; alternative dark and white bands (gneissose structure).	Composed of quartz, feldspar, biotite, hornblends, etc.	Not commonly used because of deleterious constituents, but may be used in minor constructions if easily available. Hard gneisses may be used for construction of buildings and decorative works and also as riprap stone.	Varying composition of bands are likely to give low strength of the rocks. Widely found in India.	2.5-3.0	500-2 000	—	50-200	0.5-1.5	—	2.01 × 10 ⁵ to 4.9 × 10 ⁵
3.	Quartzite	White, grey, yellowish & brownish grey, buff (colour is dependent on the impurities in the cement).	Fine to coarse grained often granular and banded.	Quartz is the chief constituent with feldspars and mica in small amounts.	Used as blocks and slabs for building stone and aggregate material.	Widely available in India.	2.55-2.65	1 500-3 000	200-600	100-300	0.2-0.6	—	9.3 × 10

4. Marble	White, rose, pink, red, green, yellow, black, etc. (Impurities impart different shades).	Fine to coarse grained, massive crystalline and granular.	Mainly calcite and dolomite or mixture of the two with some other impurities, e.g. wallastonite and serpentine as bands and veins.	Used as blocks, slabs and tiles in monuments, temples, commercial buildings. Coloured marbles are as ornamental stones.	Marbles may contain serpentine band, valuable for decorative works.	2.6-2.7	1 000-2 500	150-300	70-200	2-4	6.7-11.7	—
5. Khondalite	Light grey to brown and light pink.	Medium to fine grained; often banded or schistose.	Composed of quartz, feldspar, garnet and sillimanite, with biotite and muscovite.	Khondalite is widely used for building stones in commercial and institutional buildings in the form of blocks and slabs. In ancient times it was used in monuments and temples.	Khondalite may contain softer schistose bands and are found to weather easily on exposure to atmospheric condition. It is easily available all along the Eastern Ghats.	2.36-2.51	—	—	—	—	—	—
6. Slate	Dark grey, black, greenish grey, purple grey, etc.	Fine grained, slaty cleavage, fissile along planes of original bedding.	Composed of quartz, mica and clay minerals.	Used as slabs and roofing tiles in the construction of buildings, pavements, etc.	Easily cut into slabs, of desired dimensions. It may contain softer bands. Slate is found in many parts of the country.	2.6-2.7	1 000-2 000	—	70-200	0.1-1.6	—	—
7. Phyllite	Grey, greenish, buff, reddish. Rock characterised by a shining silky lusture (phyllitic sheen).	Fine grained, often characterised by foliation, cleavage and bedding.	Composed of micas (commonly sericite), quartz, garnet, and alusite, clay minerals and iron oxide.	Used as slabs roofing tiles for minor construction works and also carving statues in temples.	The rock is fissile. Harder phyllites (almost nearing to slates) are used commonly where their occurrence is abundant.	2.6-2.8	—	—	—	—	—	—
8. Schists	Grey to black, brown, purple and greenish grey.	Fine to coarse grained, schistose.	Consists of quartz, feldspar, biotite, muscovite, chlorite, hornblende, garnet, etc.	Not generally used, because of its low strength, but if easily available may be used for minor construction. There are different types of schists, quartz-muscovite-quartz-sericite schists, hornblende-schists, etc.	do	2.31-3.04	400-950	—	—	—	—	1.8 × 10 ⁵ to 3.4 × 10 ⁵

Note — These values are only for guidance. The exact data is being collected and these values will be revised.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publication), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'.

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones: 323 01 31, 323 33 75, 323 94 02

Telegrams: Manaksanstha
(Common to all offices)

Regional Offices:

Telephone

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

323 76 17, 323 38 41

Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Maniktola
CALCUTTA 700054

{ 337 84 99, 337 85 61
{ 337 86 26, 337 91 20

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

{ 60 38 43
{ 60 20 25

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113

{ 235 02 16, 235 04 42
{ 235 15 19, 235 23 15

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
MUMBAI 400093

{ 832 92 95, 832 78 58
{ 832 78 91, 832 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.
COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI.
HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR.
PATNA. PUNE. THIRUVANANTHAPURAM.