

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan


“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 1838-2 (1984): preformed fillers for expansion joint in concrete pavement and structure (non extruding and resilient type) Part 2 CNSL Aldehyde resin and coconut pith - Specification [CED 13: Building Construction Practices including Painting, Varnishing and Allied Finishing]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 1838 (Part 2) - 1984

Indian Standard

**SPECIFICATION FOR PREFORMED FILLERS
FOR EXPANSION JOINT IN CONCRETE
PAVEMENT AND STRUCTURE
(NON-EXTRUDING AND RESILIENT TYPE)**

PART 2 CNSL ALDEHYDE RESIN AND COCONUT PITH

(Second Reprint JUNE 1996)

UDC 625.848.074:624.078.38

© Copyright 1985

**BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002**

Indian Standard

SPECIFICATION FOR PREFORMED FILLERS FOR EXPANSION JOINT IN CONCRETE PAVEMENT AND STRUCTURE (NON-EXTRUDING AND RESILIENT TYPE)

PART 2 CNSL ALDEHYDE RESIN AND COCONUT PITH

Building Construction Practices Sectional Committee, BDC 13

Chairman

SHRI C. P. MALIK
C-4/38, Safdarjung Development Area,
New Delhi 110016

Members

SHRI P. D. AGARWAL

SHRI R. K. MATHUR (*Alternate*)

SHRI D. R. BATLIVALA

SHRI B. K. CHAKRABORTY

SHRI S. M. GORI (*Alternate*)
CHIEF ENGINEER (BLDGS)

SUPERINTENDING ENGINEER
(SPECIAL BUILDING CIRCLE)
(*Alternate*)

CHIEF ENGINEER-CUM-ADDITIONAL
SECRETARY (BR)

EXECUTIVE ENGINEER (*Alternate*)
CHIEF ENGINEER (TRAINING)

SUPERINTENDING ENGINEER
(TRAINING) (*Alternate*)

SHRI K. DEVARAJAN

SHRI A. V. GOPALKRISHNA (*Alternate*)
DIRECTOR, ARCHITECTURE

JOINT DIRECTOR, ARCHITECTURE
(*Alternate*)

Representing

Public Works Department, Government of Uttar
Pradesh, Lucknow

Bhabha Atomic Research Centre, Bombay
Housing and Urban Development Corporation
Ltd, New Delhi

Public Works Department, Government of Tamil
Nadu, Madras

Public Works Department, Government of
Rajasthan, Jaipur

Central Public Works Department, New Delhi

Engineer-in-Chief's Branch, Army Headquarters,
New Delhi

Research, Designs and Standards Organization
(Ministry of Railways), Lucknow

(Continued on page 2)

© Copyright 1985

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 1838 (Part 2) - 1984

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI S. S. GILL	Public Works Department, Government of Punjab, Chandigarh
SHRI M. KARTIKAYAN	Builders' Association of India, Bombay
SHRI R. L. KUMAR	Institution of Surveyors, New Delhi
SHRI G. V. PATWARDHAN (<i>Alternate</i>)	
SHRI M. Z. KURIEN	Tata Consulting Engineers, Bombay
SHRI G. K. MAJUMDAR	Hindustan Prefab Ltd, New Delhi
SHRI H. S. PASRICHA (<i>Alternate</i>)	
SHRI R. C. MANGAL	Central Building Research Institute (CSIR), Roorkee
SHRI J. S. SHARMA (<i>Alternate</i>)	
SHRI B. V. B. PAI	Concrete Association of India, Bombay
SHRI P. SRINIVASAN (<i>Alternate</i>)	
SHRI P. K. PANDARE	State Bank of India, Bombay
SHRI K. S. PRUTHI	Forest Research Institute and Colleges, Dehra Dun
SHRI S. G. RANADIVE	Indian Institute of Architects, Bombay
SHRI RUMMY SHROFF (<i>Alternate</i>)	
REPRESENTATIVE	Bureau of Public Enterprises, Ministry of Finance
REPRESENTATIVE	Central Road Research Institute, New Delhi
REPRESENTATIVE	Life Insurance Corporation of India, Bombay
DEPUTY CHIEF ENGINEER (NORTH) (<i>Alternate</i>)	
SHRI K. S. SRINIVASAN	National Buildings Organization, New Delhi
DEPUTY DIRECTOR (<i>Alternate</i>)	
SHRI SUSHIL KUMAR	National Buildings Construction Corporation Ltd, New Delhi
SHRI S. R. TAMBE	Public Works & Housing Department, Bombay
SHRI B. T. UNWALLA	The Institution of Engineers (India), Calcutta
SHRI G. VENKATESULU	Ministry of Shipping & Transport (Roads Wing)
SHRI M. V. SASTRY (<i>Alternate</i>)	
SHRI G. RAMAN, Director (Civ Engg)	Director General, ISI (<i>Ex-officio Member</i>)

Secretary

SHRI A. K. SAINI
Assistant Director (Civ Engg), ISI

Joints in Structure Subcommittee, BDG 13 : 14

Convener

SHRI HARISH CHANDRA Central Public Works Department, New Delhi

Members

SHRI J. P. BAJAJ	Institution of Surveyors, New Delhi
LT-COL C. T. CHARI	Engineer-in-Chief's Branch, Army Headquarters, New Delhi
SHRI R. C. P. CHOUDHARY	Engineers India Ltd, New Delhi
SHRI K. N. SINHA (<i>Alternate</i>)	
SHRI DATTA MALIK	Indian Institute of Architects, Bombay

(Continued on page 6)

Indian Standard

SPECIFICATION FOR PREFORMED FILLERS FOR EXPANSION JOINT IN CONCRETE PAVEMENT AND STRUCTURE (NON-EXTRUDING AND RESILIENT TYPE)

PART 2 CNSL ALDEHYDE RESIN AND COCONUT PITH

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 28 May 1984, after the draft finalized by the Building Construction Practices Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Joints are required in concrete roads and runways to relieve stresses developed in the slab by temperature and moisture changes. To provide an even riding surface these joints must be filled and at the same time the materials used for filling should permit expansion and contraction of concrete slab. This standard covers use of CNSL aldehyde resin and coconut pith as preformed fillers. Use of bitumen-impregnated fibre is covered in IS : 1838 (Part 1)-1983*.

0.3 To make the joint effective it is also necessary to prevent the ingress of water or grit down the joint. This is achieved by using a sealing compound over the joint filler. The requirements of sealing compound are covered by IS : 1834-1984†.

0.4 This Indian Standard is based on the work done by the Central Building Research Institute, Roorkee.

0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960‡. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Specification for preformed fillers for expansion joint in concrete pavement and structure (non-extruding and resilient type): Part 1 Bitumen-impregnated fibre (*first revision*).

†Specification for hot applied sealing compounds for joint in concrete (*first revision*).

‡Rules for rounding off numerical values (*revised*).

IS : 1838 (Part 2) - 1984

1. SCOPE

1.1 This standard specifies the material, manufacture, properties and tests for CNSL aldehyde resin and coconut pith based fillers for expansion joints in concrete roads, runways, bridges and other structures.

2. MATERIAL

2.1 Cashewnut Shell Liquid (CNSL) — Aldehyde Resin — Materials required are CNSL (*see* IS : 840-1964*), phosphoric acid (*see* IS : 6818-1973†), paraformaldehyde (*see* IS : 5271-1978‡), calcium hydroxide [*see* IS : 1540 (Part 2)-1978§], fufuraldehyde and rubber latex.

2.2 Coconut Pith — Dry coconut pith and baby fibre are used as fillers. These are bye products of coir industry.

3. MANUFACTURE

3.1 CNSL is polymerized by heating in presence of acid to a suitable consistency. The polymerized liquid is mixed with coconut pith, calcium hydroxide and hardeners — paraformaldehyde and fufuraldehyde in suitable proportions.

The mixture is filled in wooden mould and consolidated by pressing to a density of about 450 g/mm³. Slabs of 12 mm thickness are made from this and allowed to harden to achieve sufficient strength

Hardening may be accelerated by curing in a warm chamber. The flexural strength of slabs may be increased by replacing part of filler by baby fibre and crumbling under compression may be reduced by incorporating suitable proportions of rubber latex.

4. PROPERTIES

4.1 Preformed slabs or strips of expansion joint fillers shall not be deformed or broken by twisting, bending or other handling when exposed to atmospheric conditions. Pieces of the joint filler that have been damaged shall be rejected.

4.2 Recovery — When tested in accordance with IS : 10566-1983||, the specimen shall recover at least 70 percent of its thickness before the test.

4.3 Compression — The load required to compress the test specimen (*see* IS : 10566-1983||), to 50 percent of its thickness before test, shall be 0.7 to 5.3 N/mm². The material after compression shall not show a loss of more than 5 percent of its original mass.

*Specification for cashewnut shell liquid (CNSL) (*revised*).

†Code of safety for phosphoric acid.

‡Specification for paraformaldehyde.

§Specification for quick lime and hydrated lime for chemical industries: Part 2 Hydrated lime (*second revision*).

||Method of test for preformed fillers for expansion joints in concrete paving and structural construction.

4.4 Extrusion — When tested in accordance with IS : 10566-1983*, with three edges restrained; and compressed to 50 percent of its thickness before test, the extrusion of the edge of the test specimen shall not exceed 6.5 mm.

4.5 Weathering — When tested in accordance with IS : 10566-1983*, test specimen shall show no disintegration.

5. DIMENSIONS

5.1 The dimensions of fillers shall conform to those as specified in contract or order.

5.2 Tolerances of ± 2.5 mm on thickness, ± 5 mm on depth and ± 7.5 mm in length shall be permitted.

6. MARKING

6.1 The packages shall be marked with the manufacturer's name or trade-mark, if any and size.

6.2 BIS Certification Marking

The product may also be marked with Standard Mark.

6.2.1 The use of the Standard Mark is governed by the provisions of Bureau of Indian Standards Act, 1986 and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

7. SAMPLING

7.1 Number of Samples — One representative sample shall be selected from each lot of 100 m² of the material having same thickness. The sampling shall be done at random.

7.2 Size of Sample — Each sample shall consist of sufficient material so that five test pieces measuring 100 × 100 mm could be obtained.

7.3 Tests — All the test pieces as selected in 7.2 shall be subjected to physical requirements as specified in 4. The sample shall also be tested for dimensions and tolerances (see 5). The lot shall be accepted if all the five test pieces meet the physical and dimensional requirements; otherwise not.

*Method of test for preformed fillers for expansion joints in concrete paving and structural construction.

IS : 1838 (Part 2) - 1984

(Continued from page 2)

<i>Members</i>	<i>Representing</i>
SHRI P. S. GOKHALE	Gammon India Ltd, Bombay
SHRI K. RAJAGOPALAN (<i>Alternate</i>)	
SHRI G. B. JAHAGIRDAR	National Industrial Development Corporation Ltd, New Delhi
SHRI M. P. JAISINGH	Central Building Research Institute (CSIR), Roorkee
SHRI R. K. JAIN (<i>Alternate</i>)	
SHRI S. R. KULKARNI	M. N. Dastur & Company (P) Ltd, Calcutta
SHRI D. B. GHOSH (<i>Alternate</i>)	
DR M. NAYAK	Concrete Association of India, Bombay
SHRI P. SRINIVASAN (<i>Alternate</i>)	
SHRI Y. R. PHULL	Central Road Research Institute, New Delhi
SHRI K. L. SETHI (<i>Alternate</i>)	
SHRI R. V. RAMAMURTHY	Directorate General, Border Roads, New Delhi
SHRI R. P. SETH (<i>Alternate</i>)	
SHRI S. SEETHARAMAN	Ministry of Shipping & Transport (Roads Wing)
SHRI PRAFULLA KUMAR (<i>Alternate</i>)	
SHRI T. M. SHAH	Tirath Ram Ahuja Pvt Ltd, New Delhi
SHRI J. P. GUPTA (<i>Alternate</i>)	
SHRI K. S. SRINIVASAN	National Buildings Organization, New Delhi
SHRI A. K. LAL (<i>Alternate</i>)	
SHRI SUSHIL KUMAR	National Building Construction Corporation Ltd, New Delhi
SHRI DALJIT SINGH (<i>Alternate</i>)	
SUPERINTENDING SURVEYOR OF WORKS (CZ)	Central Public Works Department, New Delhi
SURVEYOR OF WORKS (CZ) (<i>Alternate</i>)	

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 331 01 31, 331 13 75

Telegrams: Manaksanstha
(Common to all Offices)

Regional Offices:

	Telephone
Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002	{ 331 01 31 331 13 75 36 24 99
*Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola, CALCUTTA 700054	{ 2 18 43 3 16 41 41 24 42
Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036	{ 41 25 19 41 29 16
Southern : C. I. T. Campus, MADRAS 600113	{ 6 32 92 95
†Western : Manakalaya, E9 MIDC, Marol, Andheri (East), BOMBAY 400093	

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001	{ 2 63 48 2 63 49
‡Peenya Industrial Area 1st Stage, Bangalore Tumkur Road BANGALORE 560058	{ 38 49 55 38 49 56
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003	6 67 16
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	5 36 27
53/5, Ward No. 29, R.G. Barua Road, 5th Byelane, GUWAHATI 781003	3 31 77
5-8-56C L. N. Gupta Marg (Nampally Station Road), HYDERABAD 500001	23 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	{ 6 34 71 6 98 32
117/418 B Sarvodaya Nagar, KANPUR 208005	{ 21 68 76 21 82 92
Patliputra Industrial Estate, PATNA 800013	6 23 05
T.C. No. 14/1421, University P.O., Palayam TRIVANDRUM 695035	{ 6 21 04 6 21 17

Inspection Offices (With Sale Point):

Pushpanjali, First Floor, 205-A West High Court Road, Shankar Nagar Square, NAGPUR 440010	2 51 71
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	5 24 35

*Sales Office in Calcutta is at 5 Chowringhee Approach, P. O. Princep Street, Calcutta 700072

†Sales Office in Bombay is at Novelty Chambers, Grant Road, 89 65 28
Bombay 400007

‡Sales Office in Bangalore is at Unity Building, Narasimharaja Square, 22 36 71
Bangalore 560002