

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 2096 (1992): Asbestos cement flat sheets - [CED 53: Cement Matrix Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS 2096 : 1982

भारतीय मानक

REAFFIRMED

2006

एसबैसटॉस सीमेंट की सपाट चादरें - विशिष्ट
(पहला पुनरीक्षण)

Indian Standard

ASBESTOS CEMENT FLAT SHEETS —
SPECIFICATION
(*First Revision*)

UDC 691-328-5-415

© BIS 1992

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

December 1992

Price Group 3

**AMENDMENT NO. 1 AUGUST 1997
TO
IS 2096 : 1992 ASBESTOS CEMENT FLAT SHEETS —
SPECIFICATION**

(First Revision)

(Page 1, clause 3) — Insert the following at the end:

'Pozzolanic materials , pigments and fillers which are compatible with asbestos cement may be added.'

(Page 1, Table 2) — Substitute '1 200' for '1 220' in the first column under the heading 'Width'.

(Page 3, Annex A) — Substitute '8112 : 1989' for '8112 : 1976'.

(CED 53)

Reprography Unit, BIS, New Delhi, India

FOREWORD

This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.

For the past several years asbestos cement flat sheets are being manufactured and used in India. These sheets are either water cured or humid cured.

These sheets are mainly used for external wall claddings, partitions, false ceilings, panelling, furniture and dado work.

Asbestos cement flat sheets are different from asbestos cement building boards which are more porous and flexible and are intended mainly for internal use. Asbestos building boards are covered separately in IS 2098 : 1964 'Specification for asbestos cement building boards'.

This standard was originally published in 1966. The present revision has been taken up in the light of experience gained during its use. In this revision frost cracking test, test for resistance to acidified waters, and test for water absorption and impermeability have been deleted, since it has been found that sheets fulfilling requirements for density and bending strength are weather-proof. Classification and strength of sheets have also been modified in this revision.

In formulation of this standard due weightage has been given to international co-ordination among the standards and practices prevailing in different countries in addition to relating it to the practices in the field in this country. Assistance has been derived from BS 690 (Part 2) : 1981 'Asbestos cement slates and sheets, Part 2 Specification for asbestos cement and cellulose asbestos cement flat sheets'.

The composition of the Committee responsible for the formulation of this standard is given in Annex B.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (revised)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

ASBESTOS CEMENT FLAT SHEETS — SPECIFICATION

(First Revision)

1 SCOPE

This standard lays down the requirements regarding composition, dimensions and tests of asbestos cement flat sheets (semi-compressed and fully-compressed). These sheets are different from autoclaved silica asbestos cement flat sheets which are covered in IS 13000 : 1990.

2 REFERENCES

The Indian Standards listed in Annex A are necessary adjuncts to this standard.

3 COMPOSITION

Asbestos cement flat sheets shall be made from a thorough and homogeneous mixture of ordinary Portland cement, conforming to IS 269 : 1989 or IS 8112 : 1989 or IS 12269 : 1987 or rapid hardening Portland cement conforming to IS 8041 : 1990 or Portland slag cement conforming to IS 455 : 1989 or Portland pozzolana cement conforming to IS 1489 (Parts 1 and 2) : 1991 and asbestos fibre to which other suitable fibres may be added.

NOTE — In case of Portland pozzolana cement and Portland slag cement, addition of pozzolanic materials shall not be permitted.

4 COLOURING MATTER

The sheets may be left in their natural colour or colouring matter may be added in the composition. They may receive coloured or uncoloured coating on their surface. Pigments which are embodied in asbestos cement for colouring purpose shall be of permanent colour and shall conform to the relevant Indian Standards. For guidance in ascertaining the colour and staining power of the pigments IS 5913 : 1989 may be referred to.

5 CLASSIFICATION

Asbestos cement flat sheets shall be classified in two types according to the value of minimum bending strength and density as given in Table 1.

6 GENERAL APPEARANCE AND FINISH

The finished product when delivered, shall be free from visible defects that impair its appearance or serviceability. The surface of the sheets shall be flat rectangular and shall have neatly trimmed straight and regular edges and shall be square at the corners.

Table 1 Classification of Asbestos Cement Flat Sheets

(Clause 5)

Class of Sheet	Description of Sheet	Minimum Bending Strength in N mm ²		Minimum Density g/cc
		Loading Parallel to the Fibre of Sheet	Loading at Right Angles to the Fibre of Sheet	
(1)	(2)	(3)	(4)	(5)
1	Semi-compressed	13	16	1.2
2	Fully compressed	20	28	1.6

NOTE — In case where the direction of the fibre is difficult to identify, the lower value obtained shall be more than the value of the third column and the higher value shall be not less than the corresponding value of the fourth column.

7 DIMENSIONS AND TOLERANCES

7.1 The nominal thickness of asbestos cement flat sheets shall conform to those value specified below:

3, 4, 5, 6, 8, 10, 12 and 15 mm.

7.2 The nominal lengths and widths of asbestos cement flat sheets shall conform to the values specified in Table 2.

Table 2 Nominal Dimensions of Asbestos Cement Sheets

Length	Width	
	1 220	1 220
600	×	
610		×
1 200	×	
1 220		×
1 800	×	
1 830		×
2 400	×	
2 440		×
3 000	×	
3 050		×

NOTE — By mutual agreement between the purchaser and the manufacturer the sheets may be supplied in dimensions other than specified in 7.1 and 7.2.

7.3 Tolerances

7.3.1 Tolerance on Thickness

From 3 mm to 5 mm — ± 0.5 mm

From 6 mm and above — $\pm 0.1 e$ mm

where 'e' is nominal thickness of sheet.

The maximum difference between extreme values of the thickness measurements within a sheet shall not exceed 10 percent of the maximum measured value.

7.3.2 Tolerance on Length and Width

Asbestos cement flat sheets shall not vary from the nominal dimensions for length and width specified in 7.2 by more than ± 5 mm.

7.3.3 Tolerance on Shape

7.3.3.1 Straightness of edges

The tolerance on the straightness of edges shall be not more than 2 mm/m for the relevant dimension (length or width).

7.3.3.2 Squareness of edges

The tolerance on squareness of the edge shall be not more than 3 mm/m.

8 TESTS

8.1 The samples of sheets taken as described in 9 and tested for the various characteristics shall conform to the requirements specified in 8.2 to 8.4.

8.2 Bending Strength Test

The values of bending stress which determine Class of sheet shall be not less than the values given in Table 1, when tested in accordance with 7.2 of IS 5913 : 1989.

8.3 Thickness

Carry out three measurements at one end cover width at approximately 20 mm from the edge by means of a gauge having a flat anvil of not less than 9 mm diameter accurate to measure 0.1 mm as shown in Fig. 1. The average of the three measurements shall correspond to the nominal thickness and the tolerance specified in 7.1 and 7.3 respectively.

The maximum difference between extreme values of the measurement shall be inside the tolerance given in 7.3.1.

8.4 Straightness and Squareness of Edges

Apply the edge to the relevant arm of the square.

Measure to the nearest 0.5 mm, by means of a steel rule, the greatest separation between the edge of the sheet and the arm of the square. This shall not be more than the value specified in 7.3.3.1.

8.5 Squareness of Edges

Place each of the four corners of the sheet in succession between the arms of the square keeping on the one hand the large side against the large arm and on the other hand the small side in contact with the small arm. In this position, measure the distance of the apex of the corner from the small arm of the square. This shall not be more than the value specified in 7.3.3.2.

8.6 Density

The density of the sheets shall be not less than the values specified in Table 1, when tested in accordance with 13 of IS 5913 : 1989.

9 SAMPLING

The sampling, inspection and acceptance shall be in accordance with IS 7639 : 1975. Unless otherwise agreed to between the manufacturer and the purchaser, the maximum and minimum inspection lots shall be 3 000 and 400 sheets respectively.

10 MANUFACTURER'S CERTIFICATE

The manufacturer shall satisfy himself that the sheets conform to the requirements of this standard and, if required, shall furnish a certificate to this effect to the purchaser or his representative clearly stating class of the sheet.

11 MARKING


11.1 Each sheet shall be stamped or marked by any suitable method on the surface not exposed to the weather with the following information:

- a) Class of sheet,
- b) Indication of the source of manufacture,
- c) Nominal thickness of sheet,
- d) Pictorial warning sign as given in IS 12081 (Part 2) : 1987, and
- e) Year and date of manufacture.

11.2 Each sheet may also be marked with the Standard Mark.

12 SAFETY RULES SHEET

All deliveries of asbestos cement flat sheets shall be accompanied by a safety rules sheet as given in IS 11769 (Part 1) : 1987.



All dimensions in millimetres.

FIG. 1 LOCATION FOR MEASURING THICKNESS

ANNEX A

(Clause 2)

LIST OF REFERRED INDIAN STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
269 : 1989	Ordinary Portland cement, Grade 33 (<i>fourth revision</i>)	8112 : 1976	Ordinary Portland cement, Grade 43 (<i>first revision</i>)
455 : 1976	Portland slag cement (<i>fourth revision</i>)	11769 (Part 1) : 1987	Guidelines for safe use of products containing asbestos: Part 1 Asbestos cement products
1489 (Part 1) : 1991 (Part 2) : 1991	Portland pozzolana cement: Fly ash based (<i>third revision</i>) Calcined clay based (<i>third revision</i>)	12082 (Part 2) : 1987	Recommendations for pictorial warning signs and precautionary notices for asbestos and products containing asbestos: Part 2 Asbestos and its products
5913 : 1989	Method of tests for asbestos cement products (<i>first revision</i>)		
7639 : 1975	Methods of sampling of asbestos cement products		
8041 : 1978	Rapid hardening Portland cement (<i>second revision</i>)	13000 : 1991	Silica asbestos cement flat sheets

ANNEX B

(Foreword)

CEMENT AND CONCRETE SECTIONAL COMMITTEE, CED 2

Chairman

DR H. C. VISVESVARAYA

Members

SHRI H. BHATTACHARYA

SHRI G. R. BHARTIKAR

SHRI U. N. RATH (Alternate)

DR A. K. CHATTERJEE

SHRI S. H. SUBRAMANIAN (Alternate)

CHIEF ENGINEER (DESIGN)

SUPERINTENDING ENGINEER (S & S) (Alternate)

CHIEF ENGINEER, NAVAGAM DAM

SUPERINTENDING ENGINEER, QCC

(Alternate)

CHIEF ENGINEER (RESEARCH-CUM-DIRECTOR)

RESEARCH OFFICER (CONCRETE

TECHNOLOGY) (Alternate)

DEPUTY DIRECTOR (I)

ASSISTANT DIRECTOR (EH) (Alternate)

DIRECTOR

JOINT DIRECTOR (Alternate)

DIRECTOR (CMDD) (N & W)

DEPUTY DIRECTOR (CMDD) (N W & S)

(Alternate)

SHRI K. H. GANGWAL

SHRI V. PATTABHI (Alternate)

SHRI V. K. GHANEKAR

SHRI S. GOPINATH

SHRI R. FAMILAKARAN (Alternate)

SHRI S. K. GUHA THAKURTA

SHRI S. P. SANKARANARAYANAN

(Alternate)

DR IRSHAD MASOOD

DR MOHAMMED KHALID (Alternate)

SHRI N. C. JAIN

DR S. P. GHOSH (Alternate)

JOINT DIRECTOR, STANDARDS (B & S) (CB-I)

JOINT DIRECTOR STANDARDS (B & S)

(CB-II) (Alternate)

SHRI N. G. JOSHI

SHRI P. D. KELKAR (Alternate)

SHRI D. K. KANUNGO

SHRI B. R. MEENA (Alternate)

SHRI P. KRISHNAMURTHY

SHRI S. CHAKRAVARTHY (Alternate)

SHRI C. REDDY (Alternate)

DR A. G. MADHAVA RAO

SHRI K. MANI (Alternate)

SHRI G. K. MAJUMDAR

SHRI S. O. RANGARI (Alternate)

SHRI M. K. MUKHERJEE

SHRI M. K. GHOSH (Alternate)

MEMBER SECRETARY

DIRECTOR (CIVIL) (Alternate)

SHRI NIRMAL SINGH

SHRI S. S. MIGLANI (Alternate)

SHRI R. C. PARATE

COL R. K. SINGH (Alternate)

SHRI Y. R. PHULL

SHRI S. S. SEEHRA (Alternate)

SHRI Y. R. PHULL

SHRI N. K. SINHA (Alternate)

DR C. RAJESWAR

DR S. C. AHLUWALIA (Alternate)

SHRI G. RAMDAS

SHRI R. C. SHARMA (Alternate)

SHRI S. A. REDDI

SHRI N. PRABHAKAR (Alternate)

Representing

In personal capacity (University of Roorkee, Roorkee 247 667)

Orissa Cement Limited, New Delhi

B. G. Shirke & Co, Pune

The Associated Cement Companies Ltd, Bombay

Central Public Works Department, New Delhi

Sardar Sarovar Narmada Nigam Ltd, Gandhinagar

Irrigation and Power Research Institute, Amritsar

National Buildings Organization, New Delhi

A. P. Engineering Research Laboratories, Hyderabad

Central Water Commission, New Delhi

Hyderabad Industries Limited, Hyderabad

Structural Engineering Research Centre (CSIR), Ghaziabad

The India Cements Ltd, Madras

Gannon Dunkerley & Company Limited, Bombay

Central Building Research Institute (CSIR), Roorkee

Cement Corporation of India, New Delhi

Research, Designs & Standards Organization (Ministry of Railways), Lucknow

Indian Hume Pipes Co Ltd, Bombay

National Test House, Calcutta

Larsen and Tourbo Limited, Bombay

Structural Engineering Research Centre (CSIR), Madras

Hospital Services Consultancy Corporation (India) Ltd, New Delhi

Ministry of Transport, Department of Surface Transport (Roads Wing), New Delhi

Central Board of Irrigation and Power, New Delhi

Development Commissioner for Cement Industry (Ministry of Industry), New Delhi

Engineer-in-Chief's Branch, Army Headquarters, New Delhi

Central Road Research Institute (CSIR), New Delhi

Indian Roads Congress, New Delhi

National Council for Cement and Building Materials, New Delhi

Directorate General of Supplies and Disposals, New Delhi

Gammon India Ltd, Bombay

*Members***REPRESENTATIVE**

SHRI J. S. SANGANERIA
 SHRI L. N. AGARWAL (*Alternate*)
 SHRI S. B. SURI
 SHRI N. CHANDRASEKARAN (*Alternate*)
 SUPERINTENDING ENGINEER (DESIGN)
 EXECUTIVE ENGINEER (S. M. R. DIVISION)
 (*Alternate*)
 SHRI TARWINDER SINGH
 SHRI ALOK AGARWAL (*Alternate*)
 DR H. C. VISVESVARAYA
 SHRI D. C. CHATTURVEDI (*Alternate*)
 SHRI Y. R. TANEJA,
 Director (Civ Engg)

Representing

Builders Association of India, Bombay
 Geological Survey of India, Calcutta
 Central Soil and Materials Research Station, New Delhi
 Public Works Department, Government of Tamilnadu, Madras
 Hindustan Prefab Limited, New Delhi
 The Institution of Engineers (India), Calcutta
 Director General, BIS (*Ex-officio Member*)

Secretary

SHRI J. K. PRASAD
 Joint Director (Civ Engg), BIS

Fibre Reinforced Cement Products Subcommittee, CED 2 : 3

Convener

DR C. RAJKUMAR

Members

SHRI S. K. BANERJEE
 SHRI N. G. BASAK
 SHRI P. K. JAIN (*Alternate*)
 SHRI S. N. BASU
 SHRI T. N. UBOVEJA (*Alternate*)
 DEPUTY DIRECTOR (I)
 SHRI A. G. DHONGADE (*Alternate*)
 SHRI S. GANAPATHY
 SHRI K. P. GOENKA
 SHRI I. P. GOENKA (*Alternate*)
 JOINT DIRECTOR STANDARDS (B & S)/CB-I
 JOINT DIRECTOR (STANDARDS) (B & S)/
 CB-II (*Alternate*)
 DR KALYAN DAS
 SHRI K. D. DHARIYAL (*Alternate*)
 SHRI P. S. KALANI
 SHRI T. S. SUMMI (*Alternate*)
 LT-COL KAMLESH PRAKASH
 LT COL A. K. BANGIA (*Alternate*)
 SHRI P. N. MEHTA
 SHRI V. K. KASLIWAL (*Alternate*)
 SHRI MOTWANI GURBUX
 SHRI H. R. OZA (*Alternate*)
 SHRI V. PATTABHI
 SHRI A. K. GUPTA (*Alternate*)
 SHRI S. PRAKASH
 DR N. RAGHAVENDRA
 SHRI RAJ KUMAR
 SHRI S. C. KUMAR (*Alternate*)
 REPRESENTATIVE
 SHRI SRINIVASAN N. IYER
 DR V. G. UPADHYAYA (*Alternate*)
 SUPERINTENDING SURVEYOR OF WORKS (CZ)
 SURVEYOR OF WORKS (CZ) (*Alternate*)
 SHRI S. B. SURI
 SHRI N. CHANDRASEKARAN (*Alternate*)
 SHRI U. N. VENKATESH
 SHRI K. S. RAMAKRISHNAN (*Alternate*)

National Council for Cement and Building Materials, New Delhi
 National Test House, Calcutta
 Directorate General of Technical Development, New Delhi
 Directorate General of Supplies and Disposals, New Delhi
 National Buildings Organization, New Delhi
 Ramco Industries Limited, Madras
 Sarbamangala Industries, Calcutta
 Research, Designs and Standards Organization, Lucknow
 Central Building Research Institute (CSIR), Roorkee
 Kalani Asbestos Cement Pvt Ltd, Indore
 Engineer-in-Chief's Branch, Army Headquarters, New Delhi
 Geological Survey of India, Calcutta
 All India Small Scale A. C. Pressure Pipe Manufacturer's Association, Hyderabad
 The Hyderabad Industries Limited, Hyderabad
 Municipal Corporation, Delhi
 National Council for Cement and Building Materials, New Delhi
 Development Commissioner, Small Scale Industries, New Delhi
 Indian Institute of Science, Bangalore
 Eternit Everest Limited, Bombay
 Central Public Works Department, New Delhi
 Central Soil and Materials Research Station, New Delhi
 Shri Digvijay Cement Company Limited, Bombay

Standard Mark

The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Revision of Indian Standards

Indian Standards are reviewed periodically and revised, when necessary and amendments, if any, are issued from time to time. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc : No. CED 2 (4916)

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones ; 331 01 31, 331 13 75

Telegrams : Manaksanstha
(Common to all offices)

Regional Offices :

Telephone

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

{ 331 01 31
{ 331 13 75

Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola
CALCUTTA 700054

{ 37 84 99, 37 85 61
{ 37 86 26, 37 86 62

Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036

{ 53 38 43, 53 16 40
{ 53 23 84

Southern : C. I. T. Campus, IV Cross Road, MADRAS 600113

{ 235 02 16, 235 04 42
{ 235 15 19, 235 23 15

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
BOMBAY 400093

{ 632 92 95, 632 78 58
{ 632 78 91, 632 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.
COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD.
JAIPUR. KANPUR. LUCKNOW. PATNA. THIRUVANANTHAPURAM.