

इंटरनेट

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

"जानने का अधिकार, जीने का अधिकार" Mazdoor Kisan Shakti Sangathan "The Right to Information, The Right to Live"

"पुराने को छोड नये के तरफ" Jawaharlal Nehru "Step Out From the Old to the New"

मानक

IS 2720-3-1 (1980): Methods of test for soils, Part 3: Determination of specific gravity, Section 1: Fine grained

soils [CED 43: Soil and Foundation Engineering]







111/1/201

Made Available By Public, Resource, Org



X

"ज्ञान से एक नये भारत का निर्माण″ Satyanarayan Gangaram Pitroda "Invent a New India Using Knowledge"

"ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता Bhartrhari-Nītiśatakam "Knowledge is such a treasure which cannot be stolen"





BLANK PAGE



PROTECTED BY COPYRIGHT

Indian Standard

METHODS OF TEST FOR SOILS

PART III DETERMINATION OF SPECIFIC GRAVITY

Section 1 Fine Grained Soils

(First Revision)

First Reprint APRIL 1989

UDC 624.131.431.1

© Copyright 1980

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

December 1980

Gr 2

Indian Standard

METHODS OF TEST FOR SOILS

PART III DETERMINATION OF SPECIFIC GRAVITY

Section 1 Fine Grained Soils

(First Revision)

Soil Engineering and Rock Mechanics Sectional Committee, BDC 23

Chairman	Representing
De Jagdish Narain	University of Roorkee, Roorkee
Members	
Additional Diffector, IRI	Irrigation Department, Government of Bihar, Patna
Additional Director Research (F. E.), RDSO DEPUTY DIRECTOR RESEARCH	Ministry of Railways
(SOIL MECH), RDSO (All	ernate)
PROF ALAM SINGH	University of Jodhpur, Jodhpur
COL AVTAR SINGH	Engineer-in-Chief's Branch, Army Headquarters
LT-COL V. K. KANITRAB (Alta	mate)
DR A. BANERJEE	Cemindia Co Ltd, Bombay
SHRI S. GUPTA (Alternate)	•
DR R. K. BHANDARI	Central Building Research Institute, Roorkee
CHIEF ENGINEEB (B&R)	Irrigation Department, Government of Punjab, Chandigarh
DR G. S. Dhillon (Alternate)	5
SHRI M. G. DANDAVATE SHBI N. C. DUGGUL (Alternate)	The Concrete Association of India, Bombay
SHRI A. G. DASTIDAB	In personal capacity (5 Hungerford Court, 12/1 Hungerford Street, Calcutta 700017)
DR G. S. DHILLON	Indian Geotechnical Society, New Delhi
DIRECTOR, IRI	Irrigation Department, Government of Uttar Pradesh, Roorkee

(Continued on page 2)

© Copyright 1980 BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

18:2720 (Part III/Sec 1) - 1980

(Continued from page 1)

Members

Representing

Shri A. H. Divanji	Asia Foundations & Construction (P) Ltd, Bombay
SHRIA. N. JANGLE (Alternate)	•
PROF GOPAL RANJAN	University of Roorkee, Roorkee
PROF GOPAL RANJAN	Institution of Engineers (India), Calcutta
Dr Shashi K. Gulhati	Indian Institute of Technology, New Delhi
DR G. B. RAO (Alternate)	
SHRI O. P. MALHOTRA	Public Works Department, Chandigarh Adminis- tration, Chandigarh
SHRI T. K. NATBAJAN	Central Road Research Institute, New Delhi
PRESIDENT (IMDA)	All India Instrument Manufacturers & Dealers Association, Bombay
DEPUTY SECRETARY (AIIMDA) (Alternate)
SHRI R. V. RANTHIDEVAN	Central Water Commission, New Delhi
DEPUTY DIRECTOR (CSMRS)	(Alternate)
RESEARCH OFFICER (B&RRL)	Public Works Department, Government of Punjab, Chandigarh
SHRI K. R. SAXENA	Public Works Department, Government of Andhra Pradesh, Hyderabad
Secretary	Central Board of Irrigation & Power, New Delhi
DEPUTY SECRETARY (Alternate)	0
SHBI N. SIVAGURU	Roads Wing, Ministry of Shipping & Transport
SHRI D. V. SIKKA (Alternate)	
SHRI K. S. SRINIVASAN	National Buildings Organization, New Delhi
SHRI SUNIL BERRY (Alternate)	
SUPERINTENDING ENGINEER (P&D)	Public Works Department, Government of Tamil Nadu, Madras
EXECUTIVE ENGINEER (SMRD) (Alternate)
SHRI H. C. VERMA	All India Instrument Manufacturers & Dealers Association, Bombay
SHBI H. K. GUHA (Alternate)	•
Shri S. D. Vidyarthi	Public Works Department, Government of Uttar Pradesh, Lucknow
DR B. L. DHAWAN (Alternate) SHRI G. RAMAN, Director (Civ Engg)	Director General, ISI (Ex-officio Member)

Secretary

SHEI K. M. MATHUE Deputy Director (Civ Engg), ISI

(Continued on page 8)

Indian Standard

METHODS OF TEST FOR SOILS

PART III DETERMINATION OF SPECIFIC GRAVITY

Section 1 Fine Grained Soils

(First Revision)

0. FOREWORD

0.1 This Indian Standard (Part III/Sec 1) (First Revision) was adopted by the Indian Standards Institution on 3 October 1980, after the draft finalized by the Soil and Rock Mechanics Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 With a view to establishing uniform procedures for the determination of different characteristics of soils and also for facilitating a comparative study of the results, the Indian Standards Institution is bringing out a series of standards on methods of test for soils (IS: 2720). This standard (Part III) deals with the method of test for determination of specific gravity of soils which finds application in finding out the degree of saturation and unit weight of moist soils. The unit weights are needed in pressure, settlement and stability problems in soil engineering. This standard was published in the year 1964. In view of the further work done in this field in this, as well as in other countries, the revision has been prepared so as to give the latest method of test which has separate provision for fine grained and coarse soils. The revision is being prepared in two sections: Section 1, dealing with the method for fine grained soil which is a basically laboratory method and Section 2 for fine, medium and coarse grained soils which is field method.

0.3 In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS : 2-1960*.

^{*}Rules for rounding off numerical values (revised).

IS: 2720 (Part III/Sec 1) - 1980

1. SCOPE

1.1 This standard (Part III/Sec 1) lays down the methods of test for the determination of the specific gravity of soil particle of fine grained soils (see Note).

NOTE — The method may also be used for medium and coarse grained soils if the coarse particles are grained to pass 4.75-mm IS sieve before using.

2. TERMINOLOGY

2.1 For the purpose of this standard, the definition of terms given in IS: 2809-1972* shall apply.

3. APPARATUS

3.1 The following apparatus is required:

- a) Two density bottles (pyknometers) of approximately 50 ml capacity with stoppers.
- b) A water-bath maintained at a constant temperature to within $\pm 0.2^{\circ}$ C. (If standard density bottles are used this constant temperature is 27°C.)
- c) A vacuum desiccator (a convenient size is one about 200 mm to 250 mm in diameter).
- d) A desiccator (a convenient size is one about 200 mm to 250 mm in diameter) containing anhydrous silica gel.
- e) A thermostatically controlled drying oven, capable of maintaining a temperature of 105 to 110°C.
- f) A balance readable and accurate to 0.001 g.
- g) A source of vacuum, such as a good filter pump or a vacuum pump.
- h) A spatula (a convenient size is one having a blade 150 mm long and 3 mm wide; the blade has to be small enough to go through the neck of the density bottle), or a piece of glass rod about 150 mm long and 3 mm diameter.
- j) A wash bottle, preferably made of plastics, containing air-free distilled water (see Note).
- k) A sample divider of the multiple slot type (riffle box) with 7 mm width of opening.
- m) A length of rubber tubing to fit the vacuum pump and the desiccator.

NOTE — Obtain the air-free distilled water for at least 30 minute in a container that can be sealed from the atmosphere during cooling. Take care to see that the container is strong enough to resist the reduction in pressure inside it during cooling.

*Glossary of terms and symbols relating to soil engineering (first revision).

4. PROCEDURE

4.1 The complete density bottle with stopper, shall be dried at 105 to 110° C, cooled in the desiccator and weighed to the nearest $0.001 \text{ g}(m_1)$ (see Note 1).

4.2 The 50 g sample obtained as described in the procedure for the preparation of disturbed samples for testing (see 1.5) shall if necessary be ground to pass a 2-mm IS test sieve. A 5 to 10 g subsample shall be obtained by riffling, and oven dried at 105 to 110°C (see Note 2). This sample shall be transferred to the density bottle direct from the desiccator in which it has been cooled. The bottle and contents together with the stopper shall be weighed to the nearest 0.001 g (m_3).

4.3 Sufficient air-free distilled water (*see* Note 3) shall be added so that the soil in the bottle is just covered. The bottle containing the soil and liquid, but without the stopper, shall be placed in the vacuum desiccator, which shall then be evacuated gradually. The pressure shall be reduced to about 20 mmHg. When using a water pump, because of variation in mains pressure, care shall be taken to ensure that the required vacuum is maintained. Care shall be taken during this operation to see that the air trapped in the soil does not bubble too violently, so as to prevent small drops of the suspension being lost through the mouth of the bottle. The bottle shall be allowed to remain in the desiccator for at least 1 hour until no further loss of air is apparent.

4.4 The vacuum shall be released and the lid of the desiccator removed. The soil in the bottle shall be stirred carefully with the spatula, or the bottle vibrated. Before removing the spatula from the bottle the particles of soil adhering to the blade shall be washed off with a few drops of air-free liquid. The lid of the desiccator shall then be replaced and the desiccator evacuated again.

4.5 The procedure outlined in 4.3 and 4.4 shall be repeated until no more air is evolved from the soil (see Note 4).

4.5.1 Alternately, the entrapped air can be removed by getting heating the pyknometer placed on a water-bath or sand-bath.

4.6 The bottle and contents shall then be removed from the desiccator and further air-free liquid added until the bottle is full. The stopper shall then be inserted. The stoppered bottle shall be immersed up to the neck in the constant-temperature bath for approximately 1 hour or until it has attained the constant temperature of the bath (see Note 5).

If there is an apparent decrease in volume of the liquid the stopper shall be removed and further liquid added to fill the bottle and the stopper replaced. The bottle shall then be returned to the bath and sufficient time shall be allowed to elapse after this operation to ensure that the

IS: 2720 (Part III/Sec 1) - 1980

bottle and its contents again attain the constant temperature of the bath. If the bottle is still not completely full this process shall be repeated.

4.7 The stoppered bottle shall then be taken out of the bath, wiped dry and the whole weighed to the nearest 0.001 g (m_3) .

4.8 The bottle shall then be cleaned out and filled completely with airfree liquid, the stopper inserted and then the whole immersed in the constant temperature bath for 1 hour or until it has attained the constant temperature of the bath. If there is an apparent decrease in the volume of the liquid, the stopper shall be removed and further liquid added to fill the bottle and the stopper replaced. The stoppered bottle shall then be returned to the batch and sufficient time shall be allowed to elapse after this operation to ensure that the bottle and its contents again attain the constant temperature. If the bottle is still not completely full this process shall be repeated. The bottle shall then be taken out of the bath, wiped dry and the whole weighed to the nearest 0.001 g (m_4) (see Note 6).

4.9 Two determinations of the specific gravity of the same soils sample shall be made (see Notes 7 and 8).

NOTE 1 — Standard Density Bottles — If a density bottle is used then in order to avoid distortion it should not be dried by placing it in an oven. It may be dried by rinsing with acetone or an alcohol-ether mixture and then blowing warm air through it.

Note 2 — Oven drying of the soil has been specified for convenience. If there is any reason to believe that this will change the specific gravity due to loss of water of hydration the soil should be dried at not more than 80° C. This fact should be reported.

NOTE 3 — Alternative Liquids for Specific Gravity Determination — With certain soils, for example those containing soluble salts, kerosene (paraffin oil) or white spirit may be preferred. If one of these is used, record the fact and carry out a separate experiment to determine the specific gravity of the liquid at the room temperature of the test. The equation for the specific gravity of the soil particles, G, given in 5.1 then becomes:

$$G = \frac{G_{\rm L} (m_2 - m_1)}{(m_4 - m_1) - (m_3 - m_2)}$$

where

 $G_{\rm L}$ = specific gravity of the liquid used, at the constant temperature;

- $m_1 = \text{mass of density bottle in g};$
- $m_2 = \text{mass of bottle and dry soil in g;}$
- $m_3 = \text{mass of bottle, soil and liquid in g; and}$
- $m_4 = \text{mass of bottle when full of liquid only in g.}$

Note 4 — Experience has shown that the largest source of error in the test is due to the difficulty in ensuring the complete removal of air from the sample. To obtain reliable results the soil should be left under vacuum for several hours, preferably overnight. Shaking the bottle in hand once or twice interuppting the vacuum gives quicker results. NOTE 5 — If a constant temperature room or cabinet is available then this procedure need not be carried out in a water-bath.

Note 6 — If method given in 4.8 is used to find the volume of the density bottle then the test may be carried out at any temperature provided it is constant throughout the test.

NOTE 7 — Many soils have a substantial proportion of heavier or lighter particles. Such soils will give erratic values for the specific gravity even with the greatest care in testing and a number of repeated tests may be needed to obtain a good average value.

NOTE 8 — Clean quartz and flint sands generally have a specific gravity close to 2.65; low values would suggest the presence of organic matter.

5. CALCULATION

5.1 The specific gravity of the soil particles G shall be measured at room temperature If water has been used as the air-free liquid, then the following equation shall be used:

$$G = \frac{m_2 - m_1}{(m_4 - m_1) - (m_3 - m_3)}$$

where

 $m_1 = \text{mass of density bottle in g;}$

 $m_2 = \text{mass of bottle and dry soil in g};$

 $m_8 = \text{mass of bottle, soil and water in g; and}$

 $m_{\star} = \text{mass of bottle when full of water only in g.}$

If some other air-free liquid has been used reference should be made to Note 3.

5.2 The specific gravity shall be calculated at 27°C. If the room temperature is different than 27°C, the following correction shall be done:

G' = K G

where

G' - Corrected specific gravity at 27°C, and $K = \frac{\text{Relative density of water at room temperature}}{\text{Relative density of water at 27°C.}}$

6. REPORTING OF RESULTS

6.1 The average of the values obtained shall be taken as the specific gravity of the soil particles and shall be reported to the nearest 0.01. If the two results differ by more than 0.03 the tests shall be repeated.

15:2720 (Part III/Sec 1) - 1980

(Continued from page 2)

Soil Testing Procedures and Equipment Subcommittee, BDC 23:3

Convener	Representing
PROF ALAM SINGH	University of Jodhpur, Jodhpur
Member s	
SHRI AMAR SINGH DEPUTY DIRECTOR RESEARCH (FE-II), RDSO DEPUTY DIRECTOR RESEARCH	Central Building Research Institute, Roorkee Ministry of Railways
(SM-III), RDSO (Alternate)	
DIRECTOR (CSMRS)	Central Water Commission, New Delhi
DEPUTY DIRECTOR (CSMRS) (Alternate)
PROF GOPAL RANJAN DR S. C. HANDA (Alternate)	University of Roorkee, Roorkee
DR SHASHI K. GULHATI	Indian Institute of Technology, New Delhi
SHRI H. K. GUHA SHRI H. N. BHATTACHARAYA (A	Geologists Syndicate Pvt Ltd, Calcutta
SHRI O. P. MALHOTBA	Public Works Department, Chandigarh Adminis- tration
SHRI M. D. NAIR	Associated Instruments Manufacturers (I) Pvt Ltd, New Delhi
PROF T. S. NAGARAJ (Alternate)	
SHRI N. M. PATEL	Delhi College of Engineering, Delhi
SHRI P. JAGANATHA RAO	Central Road Research Institute, New Delhi
COL AVTAR SINGH LT-COL V. K. KANITKAR (Altern	Engineer-in-Chief's Branch, Army Headquarters
SHRI S. D. VIDYARTIII	Public Works Department, Government of Uttar Pradesh, Lucknow
DR B. L. DHAWAN (Alternate)	

8

BUREAU OF INDIAN STANDARDS

Headquarters :

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI	110002
Telephones : 3 31 01 31, 3 31 13 75 Telegrams : N	/lanaksanstha
(Common to	all Offices)
Regional Offices :	Telephone
*Western ; Manakalaya, E9 MIDC, Marol, Andheri (East) BOMBAY 400093	. 6 32 92 95
†Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola, CALCUTTA 700054	36 24 99
Northern : SCO 445-446, Sector 35-C CHANDIGARH 160036	{2 18 43 3 16 41
Southern : C. I. T. Campus, MADRAS 600113	{ 41 24 42 { 41 25 19
Propola Official	(41 29 16
Drahen Unices .	60.00.40
AHMADABAD 380001	1 2 63 48
'F' Block, Unity Bldg, Narasimharaja Square, BANGALORE 560002	22 48 05
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nag. BHOPAL 462003	ar, 627 16
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	5 36 27
53/5 Ward No. 29, R. G. Barua Road, 5th Byelane, GUWAHATI 781003	
5-8-56C L. N. Gupta Marg, (Nampally Station Road), HYDERABAD 500001	22 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	{6 34 71 {6 98 32
117/418B Sarvodaya Nagar KANPUR 208005	{21 68 76 {21 82 92
Patliputra Industrial Estate, PATNA 800013	6 23 05
Hantex Bldg (2nd Floor), Rly Station Road, TRIVANDRUM 695001	52 27
Inspection Office (With Sale Point):	
Institution of Engineers (India) Building, 1332 Shivaji N PUNE 410005	agar, 5 24 35
*Sales Office in Bombay is at Novelty Chambers, Grant Road,	89 65 28
†Sales Office in Calcutta is at 5 Chowringhee Approach, P. O. Prin Street, Calcutta 700072	cep 27 68 00

Reprography Unit, BIS, New Delhi, India